



TECHNICAL DATA SHEET

PHS (HOLOGRAPHIC) SERIES - HOT STAMPING FOILS - RANGE


INTRODUCTION

- ✓ Henan Foils produces exceptional holographic hot stamp foils in a wide variety of patterns, having highest levels of brilliance and colours.
- ✓ Our holographic hot stamp series can be used for a wide range of substrates, depending of job application requested.
- ✓ Henan 's Holographic Foils can be over stamped or over laminated, also offers excellent adhesion across a large applications areas.

APPLICATIONS INCLUDE

- ✓ Ordinary paper.
- ✓ Printed, coated and uncoated paper.
- ✓ Dry and rough laminates.
- ✓ PS, PC, Acrylic and others.
- ✓ UV ink coated paper.
- ✓ Resin coated paper.
- ✓ PET film label stocks.
- ✓ PVC stickers.

CONSTRUCTION



STORAGE:

- ✓ Stamping foils should not be stored in direct sunlight, and must avoid extremes of heat and humidity.
- If storage conditions of 5-25°C and 35-60% humidity, a storage life of 12 months should be possible.

STAMPING MACHINE DETAILS:

- ✓ 90-150°C on vertical, calm shell, roll on machines / metal die.
- ✓ 150-179°C on cylinder machines.
- ✓ 200-245°C on rotary machines.



AVAILABILITY

- ✓ **PHS series:** 10 days.

Contact Henan Foils for availability of other shades.

The information contained in this data sheet is believed to be reliable, but the suitability of the products must be judged by the individual user. These specifications may be subject to change without notification or obligation. No warranty or liability for results obtained is expressed or implied.

FOIL SHOWCASE



**Any more information?
Please Contact Us!**

INTERNATIONAL OFFICE

Son Mir 41, 07184 – Calvià
Mallorca, SPAIN
M. +34 616 699 909
T. Int. +34 971 237 430
info@henanfoils.net

ASIA

T.+86 150 6780 6619
henanfoils@henanfoils.net

SOUTH AMERICA

ARGENTINA
Carlos y Emmanuel Brito Serpap
Moreno 6715 – 2° D
B1625FRK Belen de Escobar
Buenos Aires – ARGENTINA
T. +541143429583 | CUIT 20-25597755-6

CHILE

T.+569 7588 6503
M. +34 616 699 909